



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>E01C 23/06</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/20689</b> <b>(43) International Publication Date:</b> 13 April 2000 (13.04.00)
<b>(21) International Application Number:</b> PCT/GB99/03929 <b>(22) International Filing Date:</b> 25 November 1999 (25.11.99) <b>(30) Priority Data:</b> 9825967.4                      26 November 1998 (26.11.98)      GB <b>(71) Applicant (for all designated States except US):</b> ASPHALT SYSTEMS INTERNATIONAL LIMITED [GB/GB]; 1 Tilling House, Denbigh Road, Denbigh West Industrial Estate, Bletchley, Milton Keynes MK1 1RB (GB). <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> GOODHART, Jonathan, Luke, Henry [GB/GB]; Woodyared House, Potcote, Nr. Towcester, Northants NN12 8EH (GB). WIGHTMAN, Christopher, Paul, James [GB/GB]; Berrystead House, Berry End, Eversholt MK17 9EB (GB). <b>(74) Agent:</b> CAMPBELL, Patrick, John, Henry; J. A. Kemp & Co., 14 South Square, Gray's Inn, London WC1R 5LX (GB).		<b>(81) Designated States:</b> AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> <i>Upon the request of the applicant, before the expiration of the time limit referred to in Article 21(2)(a).</i>
<b>(54) Title:</b> SYSTEM FOR REPAIRING BITUMINOUS WEARING COURSES <b>(57) Abstract</b> <p>The invention provides a method for repairing a damaged area of a bituminous wearing course. The method comprises heating the damaged area, applying a liquid to the damaged area that rejuvenates damaged bitumen, adding new material to the damaged area in an amount required to level the area, and compacting the new material. The invention also provides a new composition for rejuvenating damaged bitumen. The composition may comprise an emulsifier, a heavy paraffinic distillate solvent extract, a heavy naphthenic distillate solvent extract and water.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## **SYSTEM FOR REPAIRING BITUMINOUS WEARING COURSES**

The invention relates to methods and compositions for repairing bituminous wearing courses, such as asphalt or tarmacadam roads and car parks.

### **5   Background to the invention**

Bituminous wearing courses such as asphalt are generally composed of about 94% aggregate (gravel or sand) and about 6% bitumen binder. The bitumen binder is composed of hydrocarbons and has ionic properties, which serve to bind the sand and  
10   gravel particles together.

Wearing courses deteriorate through oxidation of the bituminous binder. The oxidation process reduces the ionic properties of the bitumen, which in turn leads to release of the aggregate. The oxidised binder loses its flexibility and the surface  
15   shrinks and cracks. The effects of traffic and weather (temperature changes and moisture) speed up this process. After general release of material larger flaws appear which eventually turn into potholes.

The oxidation process accelerates other damage to the wearing course and  
20   failure of joints especially from conventional reinstatements, around ironwork and on trenchwork.

The conventional method for repair to damaged or aged asphalt and tarmacadam wearing courses comprises digging out of the asphalt by planing, saw  
25   cutting or with a jackhammer (pneumatic drill). The removed asphalt is disposed of and the area is made good with new material which then needs to be compacted and sealed with overbanding or jointing sealant. This conventional method is not ideal in respect of cost, safety, environment, sustainability and durability.

-2-

**Summary of the invention**

The invention provides an improved method for repairing a damaged area of a bituminous wearing course. The method comprises

- 5           (i)     heating the damaged area;
- (ii)    applying a liquid to the damaged area that rejuvenates damaged bitumen;
- (iii)   adding new material to the damaged area; and
- (iv)    compacting the new material.

10

The method preferably also comprises:

- (v)     applying a topcoating liquid to the repaired area which seals and binds the repair; and/or
- 15          (vi)    applying a fine aggregate to provide skid resistance.

The invention may be applied to any bituminous wearing course. The wearing course may be asphalt or tarmacadam, for example on the surface of a road, carpark, pavement, airfield, railway station platform or driveway. The method of the

20   invention is particularly suited to repairing potholes but it may, for example, equally be used to repair a trench, failed joint or failed seam.

The invention also provides a composition which can serve as the rejuvenating liquid for use in the method. The composition may comprise an

25   emulsifier, a heavy paraffinic distillate solvent extract, a heavy naphthenic distillate solvent extract, a naturally occurring mineral asphalt and water.

30

**Detailed description of the invention***The method of the invention*

In a particularly preferred form, the method of the invention comprises:

- 5 (i) heating (softening) the damaged area with an infrared heater;
- (ii) raking the damaged area;
- (iii) applying an emulsified liquid to the damaged area that rejuvenates damaged bitumen;
- (iv) further raking the damaged area;
- 10 (v) adding new material to the damaged area in an amount required to level the area;
- (vi) compacting the new material;
- (vii) applying a topcoating liquid; and
- (viii) broadcasting a fine aggregate on the repaired area.

15

The method of the invention repairs the wearing course by replacing compounds lost through oxidation (broadly speaking called maltenes) that give the bitumen its ionic properties of binding and flexibility. The rejuvenating liquid added to the damaged area contains such lost compounds. In this way, the invention  
20 recycles and rejuvenates damaged bitumen and avoids the need to dig out material from within the area to be repaired.

The heating step in the method of the invention is generally carried out using a fibre blanket infrared heater. The heating is generally to a depth of 10 mm to 100  
25 mm from the surface. The average temperature of the heated material should generally not exceed 200°C and may be from 50 to 200°C, preferably 100 to 200°C. As with all carbon structures the heat increases oxidation, but the infrared heat is not so fierce as to induce burning (which would destroy the binder's asphaltenes permanently). The heating time varies depending on the surface temperature, wind  
30 chill factor and whether the surface is damp, but may for example be from 5 to 20

-4-

min, normally about 10 min. The method of the invention can be carried out in damp conditions but should not generally be carried out in the rain or frost.

Once heated, the damaged area is generally raked. This mixes the highly oxidised top surface with the less oxidised sub-strata. This also increases the surface area of the mix. Care should be taken not to mix wearing course with base course aggregates.

The rejuvenating liquid is then applied. The application can be carried out using a standard hand sprayer. The composition of the liquid is described in detail below. The composition was specially developed for use in the method of the invention and comprises selected rejuvenating oils high in selected aromatics with good levels of polar compounds. It has a high resistance to temperature breakdown; it must be resistant to breakdown at the temperatures of up to 200°C achieved in heating step and may be resistant to breakdown at temperatures of up to 500°C. The oils in the rejuvenating liquid are emulsified with cationic slow set emulsifiers at higher than normal levels to ensure not only a very storable and stable emulsion but also to aid in a slow cure and break time. This adds greatly to the workability of the rejuvenated hot mix. The rejuvenating liquid is worked thoroughly into the mix to ensure complete coating of the heated material.

20

The next step in the process is the addition of new material, such as asphalt sand carpet. The new material added is only that which is required to level the patch, i.e. the amount of material that has been worn out of the surface. The material may also assist in knitting of the joint. In some cases, such as on hot rolled asphalt, pre-coated chippings are added and compacted into the surface to give road texture. The material is generally raked level and then compacted, e.g. by rolling. At this stage the surface, once it has cooled, is capable of accepting traffic.

However, the method of the invention generally comprises a further step of applying a topcoat of a sealer/binder to the area of repair and the area surrounding it.

-5-

This can provide a further boost of rejuvenating compounds into the top surface, but more importantly it binds and seals the surface against oxidation. The topcoat may be applied with standard bituminous distributors and/or hand spraying using standard tack pots. The chemical composition of the topcoat is described in detail below.

Two alternative binders are available for sale under the trade names GSB-78 and

- 5 GSB-88. GSB-78 is preferred because it has better storage characteristics and better rejuvenating and sealing properties. GSB-78 is naphtha based, while GSB-88 is an emulsion.

Finally, a dusting of fine aggregate (e.g. aluminium silicate) may be added to  
10 ensure good initial skid resistance. The repaired area should be left to harden for a time before opening to traffic, normally for a minimum of one hour.

There are numerous advantages to the method of the invention. In no particular order they are:

15

1. Cost. Because of the speed of the process, a two-man team (as opposed to three men normally) can cover up to 70 m<sup>2</sup> per day. In addition there is far lower asphalt cost in new material since only material to replace material lost as a result of the damage is added; in  
20 the conventional method it is also necessary to replace material that is drilled out from around the damaged area, adding costs due to the time taken to go to the dump as well as land fill charges and taxes. Against this there is the cost of the rejuvenating solution, the cost of gas to heat the damaged area, and the specialist equipment needed  
25 (heater and hotbox). In all the process has proved itself to be up to 50% cheaper than traditional methods.

2. Seamless Repairs. The resultant repair is fully bonded with the existing material by means of heat fusion. This eliminates the  
30 problem of joint failures and the problem of "cold shock" that occurs

-6-

in the conventional method when hot sealant or new material is added to cold asphalt to join the new material to the old material. There is no cutting of an edge to the old surface, no need for any kind of overbanding or joint sealing (notoriously short-lived), and no mixing of materials with different expansion and contraction rates next to each other. Furthermore, because of the application of the top coating in the method of the invention, the surface is further bonded and sealed to that adjacent to it.

5

10

15

3. Environment. There are numerous environmental advantages. The most obvious are that by recycling the existing surface there is far less new material used, that there is no dumping of discarded material, that the process is very quiet, and that its speed means that roads can be opened up far quicker than would normally be the case. In fact, because of the lack of noise, roads can be repaired at night while traffic is at its lightest without disturbance to residents. The system also eliminates the problems of "white finger" caused by pneumatic drills.

20

25

The around 94% of the wearing course that is rock or sand has an extremely long life time of many decades. Of the 6% of the wearing course that is binder, again only a small fraction is degraded and the remainder (the predominant compounds being asphaltenes) has a very long life span. By replacing only the fraction of the aromatic oil component that is lost, the method of the invention is highly efficient in material terms, and as a result effectively recreates the hydrocarbon chain.

30

4. Consistent quality. Government authorities tend to specify a range of depths for repair. This may be from 20 mm to 100 mm. All of the above are repairable using this system, and all perform equally well



-7-

since there is a standard repair quality. (The key to the understanding of the system is that asphalt operates like a bar of iron. The surface oxidises from the outside first. Unlike iron, the surface develops cracks and fissures down which the oxidation travels. The heating process penetrates down the cracks and fissures ensuring that all of the mix that has been subject to oxidation has received enough heat to become workable. Once it has been worked, the rejuvenating liquid is applied to add the missing hydrocarbon compounds.)

### *The rejuvenating liquid*

10

The rejuvenating liquid generally comprises compounds that have been lost from the bitumen in the damaged area, which are broadly speaking maltenes. Application of the liquid to the damaged area leads to replacement of the lost compounds and hence restores the bitumen to its original state. The rejuvenating liquid is generally rich in polar compounds, and replacement of the lost polar compounds restores that ability of the bitumen to bind the sand or gravel in the wearing surface.

15

The rejuvenating liquid preferably contains from 30 to 80 parts by weight in total of the heavy paraffinic distillate solvent extract and the heavy naphthenic distillate solvent extract, from 10 to 60 parts by weight of water, and from 1 to 5 parts by weight of the emulsifier. More preferably, the liquid comprises from 60 to 65 parts by weight in total of the heavy paraffinic distillate solvent extract and the heavy naphthenic distillate solvent extract, from 30 to 35 parts by weight of water and from 1 to 5 parts by weight of the emulsifier.

20

25

A particularly preferred rejuvenating liquid is one that we have named "GSB-99". The composition of GSB-99 is as follows:

<u>Product</u>	<u>% by Weight</u>
Aromatic Oil - Solvent	60-65%
Extract	
Heavy Paraffinic Distillate	
Solvent Extract	CAS Registry #64742-04-7
5 Heavy Naphthenic Distillate	
Solvent Extract	CAS Registry #64742-11-6
Water (H <sub>2</sub> O)	30-35%
Emulsifier	up to 5%
10	
CAS = Chemical Abstract Service	

*The topcoat*

- 15 As mentioned above, a topcoat may be applied to the repaired area. The topcoat composition may provide a further boost of rejuvenating compounds into the top surface, but more importantly it binds and seals the surface.

20 The topcoat preferably comprises gilsonite, a naturally occurring mineral asphalt (99% pure) that combines exceptional binding and adhering qualities. The topcoat preferably also comprises asphalt, cement, solvent and anti-stripping agent (cohesion agent). The solvent may comprise petroleum kerosene/naphtha, UM&P naphtha and/or lactol spirits. The amounts of these components may be as follows: gilsonite and asphalt cement - 20 to 60 parts by weight; solvents - 20 to 80 parts by weight; anti-stripping agent - 1 to 5 parts by weight. As mentioned above, a particularly preferred topcoat is sold under the trade name GSB-78, which has the following composition:

25

<u>Product</u>		<u>% by Weight</u>
Gilsonite and	CAS Registry #12002-43-6	35-45%
Asphalt Cement	CAS Registry #8052-42-4	
Solvents:		50-60%
Petroleum Kerosene/Naptha	CAS Registry #8008-20-6	
	CAS Registry #64741-41-9	
5 VM&P Naptha	CAS Registry #8032-32-4	
Lactol Spirits	CAS Registry #64742-89-8	
Anti-stripping agent		up to 5%

10 In order to produce GSB-78, the components are put together in a blend tank and agitated until homogenous and the gilsonite has dissolved.

CAS - Chemical Abstract Service

### Experimental section

15

The following experiments serve to illustrate the invention. The objective of the experiments was to compare the technical integrity of repairs carried out by the method of the invention with repairs carried out by conventional methods.

#### 20 *Fieldwork and Laboratory Testing*

Work commenced on the first area of approximately 1.5 x 2.0 meters by heating the area with an infra-red heater. Because of the ambient temperatures and previous showers the heating took slightly longer (18 mins) than normal. The  
25 average temperature of the heated material was 162°C.

The infra-red heater was then moved along to the next adjoining area. The heated material was hand raked, GSB-99 rejuvenator was sprayed evenly on to the

-10-

surface for 10 seconds, and hot rolled asphalt carpet material was then added. The material was then reworked to ensure a level surface with the addition of pre-coated chippings. The rejuvenated patch was then compacted with a dynapac 82 (trade name) vibrating roller.

- 5 Work was then carried on using the same method for a further six sections until the rejuvenation of the area (17 m<sup>2</sup>) was complete. Total time for the work was 2¾ hours.

The finished surface was then sprayed with GSB 78 Gilsonite Sealer and a  
10 fine aggregate hand applied to give instant skid resistance to the patch.

During the course of the work a sample of non-rejuvenated material and a sample of rejuvenated material were taken for analysis. Temperature measurements were taken of the heated material and also prior to rolling. Nuclear density tests were  
15 carried out before applying GSB78 Gilsonite Sealer. Cores were extracted from the area of the patch and also from an area of conventional hot rolled asphalt patch two days after.

Testing carried out in the laboratory included composition, binder, recovery,  
20 softening point, penetration of the non-rejuvenated and rejuvenated material, and density tests on the recovered cores to compare these with the in situ density tests.

#### *Discussion of the Site and Laboratory Test Results*

- 25 Composition analysis of the sample of existing material shows that it complies to British Standard 594 (BS 594): Part 1: 1992 Type F wearing course (30/14) column 6/4 Schedule 1. Analysis of the rejuvenated material shows there is an increase in binder/filler and fines content. This relates to the added binder GSB99 and hot rolled asphalt sand carpet. The rejuvenated material meets the requirement  
30 of BS594: Part 1: 1992 Type F wearing course (30/14) column 6/4 Schedule 1.

-11-

Results from the recovered binder of the existing material show a penetration of 18dmm and a softening point of 77.6°C. After rejuvenation the penetration has increased to 27dmm with the softening point 68°C.

The use of the nuclear density meter on site was to establish whether there were any variations in the compacted rejuvenated material. The results showed compaction to be consistent but where the trench material had been incorporated the density was slightly lower possibly due to the use of a softer binder. Densities of the cores from the patch compared well with the core density of the conventional hot rolled patch.

Results from the Nottingham Asphalt Tester (NAT) showed the conventional asphalt reinstatement patch to have a stiffness modulus of 870 MPa. From experience this is lower than normal, possibly due to a softer binder within the material. The average Stiffness Modulus of results from the rejuvenated patch cores was 1590 MPa. In the area where the trench reinstatement was rejuvenated the results were slightly lower at 700 MPa but this area was suspected to contain a cut back bitumen.

### *Conclusion*

Interpretation of the test results from the sampled material prior to and after rejuvenation shows a good improvement of the binder softening point and penetration. Results from the core samples show an increase of 55% in the stiffness modulus compared to the conventional hot rolled asphalt patch. The density of the material has an average of 2.236 with no visible signs of air voids. Overall the patching system of the invention would appear to be very acceptable with regard to test results. Visually the rejuvenated area was very good with the hot bond to existing material showing no visual joints - this has the advantage of instantly sealing the surface eliminating any possible fretting of the joints. The use of fine aggregate gave the patch an immediate enhanced skid resistance.

-12-

CLAIMS

1. A method for repairing a damaged area of a bituminous wearing course,  
which method comprises
  - 5 (i) heating the damaged area;
  - (ii) applying a liquid to the damaged area that rejuvenates damaged bitumen;
  - (iii) adding new material to the damaged area; and
  - (iv) compacting the new material.
- 10 2. A method according to claim 1, wherein the damaged area is raked after heating and before applying the rejuvenating liquid so as to mix highly oxidised top surface material with less oxidised sub-strata.
- 15 3. A method according to claim 1 or 2, wherein a topcoat is applied after the compacting step so as to seal the surface of the repaired area.
4. A method according to claim 1, 2 or 3 wherein the bituminous wearing course is asphalt or tarmacadam.
- 20 5. A method according to any one of the preceding claims, wherein the bituminous wearing course is a road, carpark, pavement, airfield, railway station platform or driveway.
- 25 6. A method according to any one of the preceding claims, wherein the damaged area is a pothole, trench, failed joint or failed seam.
7. A method according to any one of the preceding claims, wherein the heating is effected with an infrared heater.

30

8. A method according to any one of the preceding claims, wherein the rejuvenating liquid comprises compounds which have been lost from the bitumen in the damaged area.
9. A method according to any one of the preceding claims, wherein the rejuvenating liquid comprises maltenes.
10. A method according to any one of the preceding claims, wherein the rejuvenating liquid is rich in polar compounds.
- 10 11. A method according to any one of the preceding claims, wherein the rejuvenating liquid contains an emulsifier.
12. A method according to any one of the preceding claims, wherein the rejuvenating liquid contains a heavy naphthenic distillate solvent extract.
- 15 13. A method according to any one of the preceding claims, wherein the rejuvenating liquid contains a heavy paraffinic distillate solvent extract.
14. A method according to any one of the preceding claims, wherein the rejuvenating liquid contains an emulsifier, a heavy paraffinic distillate solvent extract, a heavy naphthenic distillate solvent extract and water.
- 20 15. A method according to claim 3, wherein the topcoat comprises gilsonite, asphalt, cement, solvent and anti-stripping agent.
- 25 16. A composition suitable for rejuvenating a damaged area of a bituminous wearing course, comprising an emulsifier, a heavy paraffinic distillate solvent extract, a heavy naphthenic distillate solvent extract and water.
- 30 17. A composition according to claim 16, comprising from 30 to 80 parts by

weight in total of the heavy paraffinic distillate solvent extract and the heavy naphthenic distillate solvent extract, from 10 to 60 parts by weight of water, and from 1 to 5 parts by weight of the emulsifier.

18. A composition according to claim 17, comprising from 60 to 65 parts by weight in total of the heavy paraffinic distillate solvent extract and the heavy naphthenic distillate solvent extract, from 30 to 35 parts by weight of water and from 1 to 5 parts by weight of the emulsifier.
19. A composition according to any one of claims 16 to 18, which is obtainable by mixing the emulsifier and water together, and then blending the resulting solution in an emulsion mill with the heavy paraffinic distillate solvent extract and the heavy naphthenic distillate solvent extract.



## INTERNATIONAL SEARCH REPORT

Intern. and App. No.

PCT/GB 99/03929

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 E01C23/06

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 E01C C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X Y A	US 4 601 605 A (DAMP STEPHEN P ET AL) 22 July 1986 (1986-07-22) abstract column 1, line 10 - line 20	1,2,4-6 7 3,7-14, 16
X A	US 4 300 853 A (JONES GEORGE M) 17 November 1981 (1981-11-17) abstract column 2, line 10 - line 38	1,2,4-6 3,7-15
Y	WO 93 17185 A (ARTEC EQUIP CO LTD) 2 September 1993 (1993-09-02) abstract page 11, line 15 - line 17	7
	-/-	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

15 February 2000

Date of mailing of the international search report

22/02/2000

Name and mailing address of the ISA

European Patent Office, P.B. 6818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

Blommaert, S

# INTERNATIONAL SEARCH REPORT

Intern. Pat. Appl. No.

PCT/GB 99/03929

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 567 222 A (HAGENBACH GERMAIN ET AL) 28 January 1986 (1986-01-28) abstract column 4, line 61 -column 5, line 13	8-16, 18
A	US 5 296 264 A (BLACKLIDGE RONALD W ET AL) 22 March 1994 (1994-03-22) the whole document	8-16, 18

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Intern. Pat. App. No.

PCT/GB 99/03929

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4601605 A	22-07-1986	NONE	
US 4300853 A	17-11-1981	NONE	
WO 9317185 A	02-09-1993	CA 2061682 A AT 184343 T AU 3489493 A BR 9305943 A CN 1076749 A CZ 9402009 A DE 69326326 D EP 0628110 A HU 67616 A JP 7506160 T MX 9300928 A NZ 249074 A PL 174227 B US 5472292 A US 5791814 A	22-08-1993 15-09-1999 13-09-1993 21-10-1997 29-09-1993 15-11-1995 14-10-1999 14-12-1994 28-04-1995 06-07-1995 31-08-1994 24-04-1997 30-06-1998 05-12-1995 11-08-1998
US 4567222 A	28-01-1986	FR 2528439 A AT 24537 T AU 557742 B AU 1560283 A AU 582284 B AU 6468186 A BE 897006 A BR 8303074 A CA 1209293 A CH 661051 A DK 263783 A EP 0096638 A ES 523133 A IT 1164261 B JP 1013743 B JP 1527650 C JP 59004648 A NO 832104 A,B, US 4554313 A	16-12-1983 15-01-1987 08-01-1987 15-12-1983 16-03-1989 29-01-1987 03-10-1983 31-01-1984 05-08-1986 30-06-1987 11-12-1983 21-12-1983 16-03-1984 08-04-1987 08-03-1989 30-10-1989 11-01-1984 12-12-1983 19-11-1985
US 5296264 A	22-03-1994	US 5503871 A	02-04-1996